

V00637

TUFFlex Premium Plus XC Banding Film

12 Micron / 47 Gauge / 0.53 Mil

70-80 Gauge Alternative

Not intended as limiting specifications

CHARACTERISTICS	VALUES
Manufacturing Process	Smart-layered Cast
Thickness (nominal)	12 Micron / 47 Gauge / 0.47 Mil
Film Width (inches)	5"
Length (feet)	1000'
Net Weight / Roll (lbs. – nominal)	.94 lbs.
Roll Diameter (O.D., inches)	2.5 inch
Core I.D.	1.12 inch

TESTS	METHODS	VALUES
Ultimate Tensile MD (PSI)	ASTM D 882	1100 PSI
Ultimate Tensile TD (PSI)	ASTM D 882	970 PSI
Elongation MD (%)	ASTM D 882	340
Elongation TD (%)	ASTM D 882	280
Tear Resistance MD (grams)	ASTM D 1922	370
Tear Resistance TD (grams)	ASTM D 1922	280
Puncture Resistance (in-lbs.)	ASTM D 4649	151 g
Ultimate Prestretch (%)	Mfg. / Highlight	390
Cling (in to out, grams)	Mfg. method	180 g

TUFFlex™

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd. NE, Suite 1700 | Atlanta, GA 30328 | U.S.A.

 Veritiv

V00638

TUFFlex Premium Plus XC Banding Film

10.2 Micron / 42 Gauge / 0.42 Mil

60 Gauge Alternative

Not intended as limiting specifications

CHARACTERISTICS	VALUES	
Manufacturing Process	Smart-layered Cast	
Thickness (nominal)	10.2 Micron / 42 Gauge / 0.42 Mil	
Film Width (inches)	5"	
Length (feet)	1000'	
Net Weight / Roll (lbs. – nominal)	.84 lbs.	
Roll Diameter (O.D., inches)	2.77 inch	
Core I.D.	1.12 inch	

TESTS	METHODS	VALUES
Ultimate Tensile MD (PSI)	ASTM D 882	1300 PSI
Ultimate Tensile TD (PSI)	ASTM D 882	1640 PSI
Elongation MD (%)	ASTM D 882	270
Elongation TD (%)	ASTM D 882	170
Tear Resistance MD (grams)	ASTM D 1922	360
Tear Resistance TD (grams)	ASTM D 1922	250
Puncture Resistance (in-lbs.)	ASTM D 4649	140 g
Ultimate Prestretch (%)	Mfg. / Highlight	380
Cling (in to out, grams)	Mfg. method	180 g

TUFFlex™

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd. NE, Suite 1700 | Atlanta, GA 30328 | U.S.A.

 Veritiv

V00639

TUFFlex Premium Plus XC Banding Film

15.9 Micron / 61 Gauge / 0.61 Mil

90 Gauge Alternative

Not intended as limiting specifications

CHARACTERISTICS	VALUES
Manufacturing Process	Smart-layered Cast
Thickness (nominal)	15.9 Micron / 61 Gauge / 0.61 Mil
Film Width (inches)	5"
Length (feet)	1000'
Net Weight / Roll (lbs. – nominal)	1.22 lbs.
Roll Diameter (O.D., inches)	2.55 inch
Core I.D.	1.12 inch

TESTS	METHODS	VALUES
Ultimate Tensile MD (PSI)	ASTM D 882	1240 PSI
Ultimate Tensile TD (PSI)	ASTM D 882	1180 PSI
Elongation MD (%)	ASTM D 882	350
Elongation TD (%)	ASTM D 882	290
Tear Resistance MD (grams)	ASTM D 1922	385
Tear Resistance TD (grams)	ASTM D 1922	290
Puncture Resistance (in-lbs.)	ASTM D 4649	171 g
Ultimate Prestretch (%)	Mfg. / Highlight	500
Cling (in to out, grams)	Mfg. method	180 g

TUFFlex™

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd. NE, Suite 1700 | Atlanta, GA 30328 | U.S.A.

 Veritiv

V00640

TUFFlex Premium Plus XC Banding Film

20.3 Micron / 80 Gauge / 0.80 Mil

1.2 mil replacement

Not intended as limiting specifications

CHARACTERISTICS

VALUES

Manufacturing Process	Smart-layered Cast
Thickness (nominal)	20.3 Micron / 80 Gauge / 0.80 Mil
Film Width (inches)	5"
Length (feet)	1000'
Net Weight / Roll (lbs. – nominal)	1.6 lbs.
Roll Diameter (O.D., inches)	1.02 inch
Core I.D.	3.64 inch

TESTS

METHODS

VALUES

Ultimate Tensile MD (PSI)	ASTM D 882	1720 PSI
Ultimate Tensile TD (PSI)	ASTM D 882	2640 PSI
Elongation MD (%)	ASTM D 882	290
Elongation TD (%)	ASTM D 882	330
Tear Resistance MD (grams)	ASTM D 1922	390
Tear Resistance TD (grams)	ASTM D 1922	510
Puncture Resistance (in-lbs.)	ASTM D 4649	210 g
Ultimate Prestretch (%)	Mfg. / Highlight	270
Cling (in to out, grams)	Mfg. method	180 g

TUFFlex™

tufflexpackaging.com

844-VERITIV

1000 Abernathy Rd. NE, Suite 1700 | Atlanta, GA 30328 | U.S.A.

 Veritiv